


Particle Size Distribution Report



% +3"	% Gravel		% Sand			% Fines	
	Coarse	Fine	Coarse	Medium	Fine	Silt	Clay
0.0	0.0	0.0	0.0	6.8	91.0	2.2	

SIEVE SIZE	PERCENT FINER	SPEC.* PERCENT	PASS? (X=NO)
1	100.0		
.75	100.0		
.5	100.0		
.375	100.0		
#4	100.0		
#10	100.0		
#20	99.7		
#40	93.2		
#60	37.4		
#100	5.0		
#140	2.6		
#200	2.2		

* (no specification provided)

Material Description		
Fine grained, SAND		
<div> <div> Atterberg Limits </div> <div> PL= </div> <div> LL= </div> <div> PI= </div> </div>		
<div> <div> Coefficients </div> <div> D₉₀= 0.4069 </div> <div> D₈₅= 0.3842 </div> <div> D₆₀= 0.3054 </div> <div> D₅₀= 0.2803 </div> <div> D₃₀= 0.2316 </div> <div> D₁₅= 0.1899 </div> <div> D₁₀= 0.1729 </div> <div> C_u= 1.77 </div> <div> C_c= 1.02 </div> </div>		
<div> <div> Classification </div> <div> USCS= SP </div> <div> AASHTO= </div> </div>		
<div> <div> Remarks </div> </div>		

Location: BI-PB-200-12 B
Sample Number: 6485 (27)

Depth: 2.0'

Date: 12/07/12

Thompson Engineering

Mobile, Alabama

Client: CDM/Thompson Engineering JV
Project: MsCIP Barrier Island Restoration GT

Project No: 1221110095

Figure